

Glass types available at EcoGlass for molding

Standard glass types

Glass	nd	ne	vd	ve	g/cm³	Tg	T13	T7.6	alpha 20/300
LIBA 2000+	1,52100	1,52300	58,85	58,63	2,59	504	-	686	9,4
borosilicate	1,47200	1,47400	65,38	65,25	2,23	525	558	820	3,3

High refractive index glass types (Schott)

Glass	nd	ne	vd	ve	g/cm³	Tg	T13	T7.6	alpha 20/300
P-SK58A	1,58913	1,59143	61,15	60,93	2,97	510	510	608	8,41
P-SK57Q1	1,58600	1,58835	59,50	59,26	3,01	493	494	593	8,9
P-SK60	1,61035	1,61286	57,90	57,66	3,08	507	509	606	8,85
P-LAK35	1,69350	1,69661	53,20	52,95	3,85	508	511	598	9,68
P-SF69	1,72250	1,72883	29,23	29,00	2,93	508	508	602	11,13
P-LASF47	1,80610	1,81078	40,90	40,66	4,54	530	532	627	7,27
P-LASF51	1,81000	1,81470	40,93	40,68	4,58	526	534	629	7,4

Jablonec nad Nisou

10.12.2020

[EcoGlass, a.s.](#)